

UC / UT Series

Application 應用	Product 產品	Viscosity黏度 (cps @ 25°C)	T.I 觸變值	Tg(°C) 玻璃轉化溫度	Characteristic 特性
Focus fixing bonding	UC-3207R	27000	4.3	73	Dual curable, High adhesion, High hardness, Good water proofing
Lens barrel & Lens bonding	UC-3218L	9000	4.9	36	High adhesion, Good impact resistance

Application 應用	Product	Appearance	T.I 觸變值	Tg(°C) 玻璃轉化溫度	Hardness硬度 (Shore D)	Work Life 工作時間 (Days)	Cure condition 固化條件	Characteristic 特性
Active alignment	UT-5022H	Gray	35000	6	56	2	365nm LED 3,000mJ + Convection Oven 6.0m @ 80°C	Low volume cure shrinkage, Anti flare, High adhesion
	UT-5023B	Black	51000	6	85	3	365nm LED 3,000mJ + Convection Oven 6.0m @ 80°C	Low volume cure shrinkage, Anti flare, High adhesion
	UT-5500	Black	41000	5.5	52	2	365nm LED 3,000mJ + Convection Oven 6.0m @ 80°C	High adhesion with PA and PC, Low volume cure shrinkage
	UT-5508	Black	50000	5.6	57	2	365nm LED 3,000mJ + Convection Oven 6.0m @ 80°C	High adhesion with PA and PC, Low volume cure shrinkage
	UT-5122H	Gray	50000	6	51	2	365nm LED 3,000mJ + Convection Oven 6.0m @ 70°C	Low temperature curable, High adhesion with LCP and PC, Low volume cure shrinkage
IR-filter glass/ film bonding	UT-6000	Pale yellow	10000	4	41	3	365nm LED 3,000mJ + Convection Oven 3.0m @ 80°C	Fast curable, High adhesion
	UT-5021	Transparent	14000	1	39	3	365nm LED 3,000mJ + Convection Oven 4.0m @ 90°C	Low T.I, Fume free, High adhesion